

TECHNICAL DATA SHEET

REVISED: 01/12/2022

VICEVERSA SPECIAL MS

PROFESSIONAL LINE FOR WALL COVERINGS



A modified silylated polymer adhesive created for binding structural components in the building trades, and for wallcoverings and flooring in PVC, LVT, glass fibre wallcoverings in humid environments (bathrooms, saunas etc). Low rate of elasticity.

Suitable for:

- General metalworking
- Items in polyurethane and polystyrene
- Vinyl, and glass fibre wallcoverings
- Flooring in LVT and PVC
- Installation of glass fibre wallcoverings in humid areas (bathrooms, saunas etc)

TECHNICAL FEATURES:

- + Solvent free
- + No water content
- + Low VOC (Volatile Organic Compounds)

GROUND PREPARATION

All grounds should be dry, absorbent (this product also works with non-porous grounds), solid, dust-free and free from paint or oil. Any gaps should be sealed using our two-part epoxy adhesive, EPOXY, and then smoothed.

PREPARATION OF MATERIALS

Before commencing installation, we suggest leaving the materials on site for one day prior to commencing work for acclimatisation to room temperature. Once SPECIAL MS has been applied to the wall, install the product in accordance with the manufacturer's recommended installation temperature.

PREPARATION OF PRODUCT

SPECIAL MS is a ready to use single component adhesive

PRODUCT APPLICATION

SPECIAL MS can be applied directly to the wallcovering using a nr° 1 grooved spatula. Fix the two surfaces together making sure there is contact at all points.

COVERAGE

Coverage depends on the nature of the installation. Approx 250-350g/m².

STORAGE

The product is guaranteed in its original packaging, in standard conditions (+5 °C to + 35 °C), for 12 months from date of production. It is important to keep the product in dry conditions, away from heat sources and direct sunlight.

TECHNICAL DATA SHEET

REVISED: 01/12/2022

VICEVERSA SPECIAL MS

PROFESSIONAL LINE FOR WALL COVERINGS



PACKAGING

PRODUCT CODE	WEIGHT	UNIT	TYPE OF PACKAGING	PCS IN BOX
30201 (White)	2,5	kg	Rectangular Bucket	1
30202 (Crystal)	2,5	kg	Rectangular Bucket	1

PRODUCT TECHNICAL DATA

Base	Silylated polymer
Physical appearance	White or clear
Percentage of solids	Approx 75%
Customs code	3909 5090
Operating temperature	+10°C +35°C
Wait time	None
Open time	Approx 30-40 minutes
Complete drying time	48/72 hours

CLEANING

We suggest cleaning using a nitro thinner

FINAL REGULATIONS

Keep out of reach of children and pets. Discharge the waste in special containers for building materials

DISCLAIMER

The information contained in the data sheet, based on results of our long experience, are for information only. Therefore, those who intend to use it are required to assess whether the product is suitable for their use, and to assume responsibility for its use.